

Meltio Nickel 718

Material Group: Nickel Alloys

Nickel 718 is a high-strength, corrosion-resistant nickel-chromium material used at -252°C to 705°C. Poor thermal conductivity, high toughness and strong work hardening tendency adversely affect its machinability, creating a very good business case for additive manufacturing.


Nomenclature Standards

AWS A 5.9 _____	ERNiFeCr - 2
EN ISO 14343 - A _____	S Ni 7718 (NiCr19Fe19Nb5Mo3)
Material N° _____	2.4667

Chemical Composition





Ni	C	Si	Mn	Cr	Fe	Mo	Nb	S
Base	0.02	0.2	0.2	22	1	9	3.3	<0.01

Spool Specs



Diameter	1 mm
Weight	15 kg
Volume	1829 cm ³
Density	8.2 g/cm ³
Spool Type	BS300

Applications

			
Aerospace industries	Chemical industries	Automotive industries	Energy industries

Mechanical Properties

Results show Meltio's wire LMD 3D printed specimens to perform at the same level as conventional manufacturing methods, with low deviations and near isotropic properties between horizontal (XY) and vertical (XZ) print orientations.

		Tensile Strength (MPa)	Yield Strength (MPa)	Elongation (%)	Hardness (HV-30)
Wrought Properties		1241	1034	10	342
Cast Properties		802	758	5	
Meltio As Built	XY	832 ± 50	536 ± 32	24 ± 3	303
	XZ				
Meltio Post Heat Stress Relive (TT.1)	XY	1016 ± 28	660 ± 10	18 ± 6	285
	XZ	925 ± 86	631 ± 10	15 ± 2	
Meltio Post Heat Aging (TT.1 + TT.2)	XY	1256 ± 11	1025 ± 7	11 ± 1	332
	XZ	1208 ± 49	980 ± 2	10 ± 5	

Heat Treatment

HT.1 - Solution

Heat Treatment to reduce residual stresses within component

- Heat up to 980°C in 2h
- Hold at 980°C during 1h

HT.2 - Ageing Treatment

Heat Treatment to improve material properties

- Heat up to 720°C in 2h
- Hold at 720°C during 8h
- Cool down to 620°C in 1h 50'
- Hold at 620°C during 8h

Printing Parameters Used

Print Speed	Deposition Width	Layer Height	Laser Power
450 mm/min	1 mm	1.2 mm	1100 W

Shielding gas: Argon > 99.996% purity.

Machine Used: Meltio M450

Laser System: 6x200W Fiber coupled diode lasers. 976nm wavelength.

* Data represent typical reference values from Worught (ASTM A36) and Cast (ASTM A352) material classification compared to Meltio (M450) horizontal (XY) and vertical (XZ) specimens extracted from 3D printed walls and tensile tested according to UNE EN ISO 6892-1

**Any technical information or assistance provided herein is given and accepted at your risk, and neither Meltio nor its affiliates make any warranty relating it or because of it. Neither Meltio nor its affiliates shall be responsible for the use of this information, or any product, method or apparatus mentioned, and you must make your own determination for its suitability and completeness for your own use. Specifications are subject to change without notice.